

eiDoor Rigid PVC Material Test Results
ASTM D1308-02 (07)



Eggers Industries



CLIENT: InPro Corporation
S80 W18 766 Apollo Dr
Muskego, WI 53150
Attn.: Matthew Bennett

Test Report No: 177:016620-01

Date: November 22, 2008

SAMPLE ID: Rigid PVC Material

DATE OF RECEIPT: October 29, 2008

TESTING PERIOD: November 15-22, 2008

AUTHORIZATION: Client's PO #: 65156

TESTS REQUESTED: The submitted sample was tested for Resistance to Chemicals in accordance with the procedures outlined in ASTM D1308-02 (07)

TEST RESULTS: Continued on the following pages

PREPARED BY:

Robert Strzelecki, Technician
Building Materials Lab

SIGNED FOR AND ON BEHALF OF
SGS U.S. TESTING COMPANY INC.

Dominick Lepore, Manager
Building Materials

Page 1 of 2

This document is issued by the Company under its General Conditions of Service for North America printed overleaf or accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction document. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This document can not be reproduced, except in full, without the prior written permission of SGS U.S. Testing Company Inc. Samples are not retained by the Company for more than 30 days, unless special arrangements are made.

CLIENT: InPro Corporation

RESULTS:

RESISTANCE TO CHEMICALS

ASTM D1308-02 (07)

Chemical	Discoloration	Change in Gloss	Blistering	Softening	Swelling
Distilled Water, Cold	0	0	0	0	0
Distilled Water, Hot	0	0	0	0	0
Ethyl Alcohol, 50% Vol.	0	0	0	0	0
Vinegar, 3% Acetic Acid	0	0	0	0	0
Sodium Hydroxide, 10%	0	0	0	0	0
Sulfuric Acid, 10%	0	0	0	0	0
Soap Solution, 1%	0	0	0	0	0
Detergent Solution, 1%	0	0	0	0	0
Bleach	0	0	0	0	0
Tomato Juice	1	0	0	0	0
Vegetable Oil	0	0	0	0	0
Ketchup	0	0	0	0	0
Mustard	0	0	0	0	0
Coca Cola	0	0	0	0	0
Coffee	0	0	0	0	0
Tea	1	0	0	0	0
Red Wine	0	0	0	0	0
Lubricating Oil	0	0	0	0	0
Pencil #2	1	0	0	0	0
BIC, Fine Point Pen	1	0	0	0	0
Crayon	1	0	0	0	0

Rating:

- 0 = No change
- 1 = Slight change
- 2 = Moderate change
- 3 = Severe change

Notes: Sample ID: Rigid PVC Material
 Test Procedure: 7 days Spot Test, Open Method.
 Lab Environment: Temperature 23°C, Humidity 50 %
 Specimen Conditioning: 48 hours minimum

End of Report



Stile & Rail Doors, Door Frames,
 Veneered Components, Plywood

Two Rivers Division
 One Eggers Drive
 Two Rivers, WI 54241
 Phone: 920.793.1351
 Fax: 920.793.2958

www.eggersindustries.com

Flush Doors

Neenah Division
 164 North Lake Street
 Neenah, WI 54956
 Phone: 920.722.6444
 Fax: 920.722.0357

email: sales@eggersindustries.com